



MaxLVT Antislip

High density polyethylene underlay with antislip layer designed for LVT floors with CLICK system, offering very good floor heating compatibility.

Product highlights

- Closed cells HDPE foam used for installation of LVT floors.
- Antislip surface for locking system protection.
- Suitable for floor heating.
- For high demands on pressure stability under heavy loaded floors.
- Very high material density.
- 100 % recyclable, FCKW and HFCKW free.
- Ecologically friendly.

EPLF	Category	Value/Unit	Test methods
T	Thickness	1,2 mm ± 5%	EN823
L	Length	15 000 mm ± 5%	EN822
W	Width	1 000 mm ± 5%	EN822
AW	Area weight	0,21 kg/m² ± 5%	Tested internally
QW	Density	130 kg/m³ ± 5%	Tested internally
RWS	Reflected walking sound	8' % ± 2	IHD-W431
IS	Impact sound reduction	17' dB ± 2	EN-ISO10140, ISO717-2
CS	Temporary loads resistance	200 kPa ± 10%	EN826
CC	Static loads (furniture) resistance	>50 kPa ± 10%	EN1606
DL	Dynamic loads (walking) resistance	>100 000' cycles	EN13793
PC	Local unevenness compensation	1,00 mm ± 10%	EN-ISO868
TR	Thermal insulation	0,025' m²K/W ± 0,003	EN12667:2002 at 24°C
SD	Protection against moisture	<75 m	EN12086
RLB	Protection against falling objects	600 mm	EN13329, EN438
RTF	Reaction to fire	---	EN-ISO11925-2, EN12501-1

Logistic Parameter	Sales unit	Packaging	Palette
Form	Roll	---	Cardboard
Quantity	1 Pc.	---	33 Rolls
Area	15m²	---	495m²
Weight	3,15kg ± 10%	---	103,95kg ± 10%

General information

All data are based on our experience and careful investigations. The diversity of the materials used, as well as the different construction site and processing conditions, can not be examined or influenced by us in detail. The quality and function therefore depends on the expert site evaluation and product use. In case of doubt, carry out your own tests or seek advice on our application technology. When processing, please observe the rules of technology as well as the manufacturing specifications of the building materials involved and constantly changing state of technology.

Storage

Approx. 1 year, protecting from direct sunlight or other weather influences.

Application

Remember to apply a vapor barrier of SD > 75m directly to the subfloor and seal its joints with aluminium sealing tape first. Unroll underlay on the sealed vapor barrier, with individual panels adjacent to one another and seal the joints with aluminium sealing tape.

Product informations may change without notice. Please visit our webpage for updated product informations.



*Information sur le niveau d'émission de substances volatiles dans l'air intérieur, présentée en forme de bandeau par couleur, sur une échelle de classes allant de A+ (très faible émission) à C (forte émission).

*value delivered from similar product test results